



KT Refractories US Company

Office Address: 3615 Elmridge St, Houston, TX 77025

Warehouse Address: 4583 S. Wayside Dr., Houston, TX 77087

Phone: 1877-365-2995 Fax: 713-838-2248

www.KTRefractories.com

Bio Soluble Fiber Blanket Data Sheet

Technical Items	1260/2300 SOLUBLE FIBER BLANKET			
Classification Temperature	1260°C (2300 °F)			
Max continuous working temperature	1050°C (1922 °F)			
Color	White			
Odor	Odorless			
Melting Point	1300°C (2372 °F)			
Permanent Linear Shrinkage-1000°C (1832 °F)	1.3% (24 Hours)			
Density				
kg/m ³	64	96	128	160
Lb/ft ³	4	6	8	10
Tensile Strength (kpa)	30	50	65	80
Thermal Conductivity-W/mk (BTU.in/hr/ft²/°F)				
Mean Temperature				
400°C (752°F)	0.12 (0.82)	0.10 (0.69)	0.09 (0.62)	0.09 (0.62)
600°C (1112°F)	0.18 (1.24)	0.16 (1.11)	0.15 (1.03)	0.14 (0.97)
800°C (1472°F)	0.30 (2.09)	0.25 (1.73)	0.22 (1.52)	0.20 (1.38)
1000°C (1832°F)	0.43 (2.98)	0.36 (2.49)	0.30 (2.08)	0.28 (1.93)
Typical Chemical Composition (%)				
SiO ₂	61-68			
CaO	27-32			
MgO	2-6			

The technical data herein are typical average values based on the commonly-accepted test methods and are subject to normal variations by production lots. It is supplied as a technical service and are subject to change without notice, the data contained herein should not be used for specification purposes or contractual obligation. Check with us for latest information